

TECHNICAL DATA

COMBLANCHIEN

STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Bulk density	kg/m ³	NF EN 1936		2670
Porosity	%	NF EN 1936		0.8
Flexion breaking load	Mpa	NF EN 12372		20.5

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Wear resistance	mm	NF EN 14157		19.7
		NF EN 1341		
		NF EN 1342		
Absorption by capilarity	g/(m ² xS ^{0.5})	NF EN 772-11	C//bed	
		NF EN 772-11	C_I_bed	
Compression breaking load	Mpa	NF EN 1926		203
		NF EN 772-1		
Frost resistancy	cycles	NF EN 12371		240
Slipping resistancy		NF EN 14231	Flamed	75
		NF EN 1341		
		NF EN 1342		
Anchor tie test	N			
Thermal conductivity	W/(m.k)	RT 2005		3.5

Source: CTMNC Paris

Update : 26/01/2015

Other names:

Musancy, Rocherons, Ladoix La Serrée, Corgoloin....